



Thickness: 1/4" (6.5mm) overall

Width: 8 5/8" (220 mm)

Length: 59 1/2" (1510mm)

Finish: Matte

Surface: Light Brush

Texture Embossed

Package: 21.45 sqft/carton

48 cartons/pallet

Weight: 45.53 lb/carton

20.65 kg/carton



TULIP



DAISY



LILY



CHAMOMILE



IRIS



LAVENDER




BLUEBELL



CARNATION



MARIGOLD




PEONY

A WATERPROOF EVOLUTION



100% waterproof flooring



4-sided painted micro v-bevels create real parquet look



Ultra low VOCs



1.5mm pad attached



Formaldehyde free & phthalates free



Lifetime limited residential wear warranty
*Limited conditions apply



Uniclic® click system



Pet friendly



10 years limited commercial wear warranty
*Limited conditions apply



Light Brush Texture Embossed Surface



Certified for underfloor heating system
*See installation manual for details



The most recognized Indoor Air Quality Certification

SPC FLOORING TECHNICAL DATA

Technical Characteristics	Test Method and Standards	Verdict
Size	ASTM F2055 A tolerance of $\pm 0.4\text{mm}/305\text{mm}$	Pass
Squareness	ASTM F2055 $\leq 0.25\text{mm}$	Pass
Thickness	ASTM F387-17 $\pm 0.20\text{mm}$	6.0mm
Thickness, Wear Layer	ASTM F410-08(2017) Commercial, 0.5mm min	0.5mm
Residual Indentation	ASTM F1914-18 Average $\leq 0.18\text{mm}$	0.02mm
Dimensional Stability	ASTM F2199-20 (70°C, 6h) Residential, (avg max) $\leq 0.25\%$, Commercial, (max) $\leq 0.2^\circ$	Pass
Curl	ASTM F2199-20 (70°C, 6h) $\leq 0.080\text{in}$	Pass
Resistance to Chemicals	ASTM F925-13 (2020) No more than a slight change in surface dulling, surface attack, or staining	No change
Resistance to Heat	ASTM F1514-19 (avg, max) $\Delta E^* \leq 8$	Pass
Resistance to Light	ASTM F1515-21 (avg, max) $\Delta E^* \leq 8$	Pass
Static load resistance	ASTM F970-17 For commercial only Residual indent $\leq 0.13\text{mm}$	0.01mm (no attached back)
Abrasion/Wear resistance	ASTM D4060-19 Rotation frequency: 60r/min Abrasive wheels: CS-17 Load on each wheel: 1 000g Test revolutions: 1 000	55.8mg
Castor chair resistance	NALFA/ANSIL F-11 After 25000 cycles, no delamination shall occur. No disturbance to the surface other than a slight change in appearance.	Pass
Fungi resistance	ASTMG21-15	Rating 0, none growth
Heavy metal elements	ASTM F963-16	Not Detected (less than the detection limit)
Phthalate content test (DBP/DEHP/BBP/DINP/DIBP/DPENP/DHEXP/DCHP)	CPSC-CH-C100-O 9.4	Not Detected (less than the detection limit)
Thermal conductivity	ASTM C518-21	0.107 W/(m.K)
Thermal resistance	ASTM C518-21	0.056 (m2.K)/W
Abrasion/Wear resistance	ASTM D4060-19	55.8 mg
Specific Optical Density of Smoke	ASTM E662	<450
Critical Radiant Flux	ASTM E648/ NFPA classification	Class 1