

Product quality					
Product		Chambord	Cheverny	Versailles	Wide plank
Formats		600 x 600 x 15mm	180 (82) x 296 (291) x 15 mm	800 x 800 x 15mm	1500 x 120 x 15mm
Packaging	Pack:	4 Elements / 1,44 m ² ~ 11,5 kg	8 + 16 Elements / 0,63 m ² / ~ 5,0 kg 	4 Elements / 2,56m ² / ~ 20,84 kg	8 Elements / 1,44m ² / ~ 11,83 kg
	Pallet:	32 Packs / 46,08 m ²	116 Packs / 72,5 m ²	32 Packs / 81,92 m ²	72 Packs / 103,68 m ²
Notes		- only suitable for all-over adhesion - cleaning and maintenance see instructions - technical changes reserved			
Guarantee (according to Parador guarantee conditions)		25 Years (privat area) / 10 Years (commercial use)			

Tolerances (EN 13489)	
Admissible difference in length	± 0.1 %
Admissible difference in width	± 0.2 mm
Squareness of the elements	≤ 0.2 %
Longitudinal curvature along the element	≤ 0.1 %
Transverse curvature across the width	≤ 0.2 %
Height differences of elements	≤ 0.2 mm
Moisture content at the time of first delivery	5 – 9%
Top layer	~ 3.5 mm

Product labeling				
				
EN 14342:2013		The mark of responsible forestry		

Classification				
	Test standard	Rating		
 Profile		T & G		
 Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat		
 Thermal resistance Suitable for installation over underfloor heating	EN 12664	0,11 m ² *K/W		
 Formaldehyde (E1 = 0.1 ppm)	EN 16516	≤ 0.05 ppm		
		Lacquer	Natural oiled	untreated
 Reaction to fire	EN 13501-1	Dfl-s1		Dfl-s1 (CWFT)
 Chemical resistance	EN 13442	Category 5	Category 3	NPD
Bond strength / Cross cutting test	ISO 2409	Category 1	n.n.	NPD

Free sorting according to EN 13489	
Type of wood:	Oak
Botanical name / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L., spp / QCXE
Sorting:	Natur
Features (Upper side of each lamella) „Features shall be measured according to EN 1310“	
Sound sapwood	not permitted
Knot (intergrown)	permitted: up to 15mm
Broken knots	not permitted
Falling out knot	permitted: up to 3mm also cluster of knots
Pinknots	permitted
Slight splits, hairline	permitted: no end cracks (up to 5mm)
Bark pocket	not permitted
Lightning cracks	permitted
Slope of grain	permitted
Medullary ray	permitted
Discoloration, colour variation	allowed: uniform colours with slight differences
White streaks	not permitted
Pilling sticks marking	not permitted
Biodeterioration (EN 1311)	not permitted
Non-visible parts	
All the features without restrictions on size or length permitted provided they do not affect the strength or durability of the soil.	
Comment	
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master	

Changed:	QMB	File name:	PA TDS Parkett Tafelparkett EI N3 EN 20250101
Date:	01.08.2013	Update:	https://parador.de/en/services/downloads/engineered-wood-flooring
Our TDS are constantly updated and adapted to the state of art. This version supersedes all earlier versions and is valid from:			01.01.2025