


PARADOR

Panel parquet Trendtime 11 / Trendtime 12

Product quality					
Product		Trendtime 11 Cheverny	Trendtime 12 Chambord	Trendtime 12 Versailles	Frame board
Formats		180 (82) x 296 (291) x 15 mm 8 + 16 Elements / 0,63 m² / ~ 5,0 kg	600 x 600 x 15mm 4 Elements / 1,44 m² ~ 11,5 kg	800 x 800 x 15mm 4 Elements / 2,56m² / ~ 20,84 kg	1500 x 120 x 15mm 8 Elements / 1,44m² / ~ 11,83 kg
Packaging	Pack:				
	Pallet:	116 Packs / 72,5 m²	32 Packs / 46,08 m²	32 Packs / 81,92 m²	72 Packs / 103,68 m²
Notes		- only suitable for all-over adhesion - cleaning and maintenance see instructions - technical changes reserved			
Guarantee (according to Parador guarantee conditions)		25 Years (privat area) / 10 Years (commercial use)			
Tolerances (EN 13489)					
Admissible difference in length		± 0.1 %			
Admissible difference in width		± 0.2 mm			
Squareness of the elements		≤ 0.2 %			
Longitudinal curvature along the element		≤ 0.1 %			
Transverse curvature across the width		≤ 0.2 %			
Height differences of elements		≤ 0.2 mm			
Moisture content at the time of first delivery		5 – 9%			
Top layer		~ 3.5 mm			
Product labeling					
					
Classification					
		Test standard	Rating		
	Profile		T & G		
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chairmat		
	Thermal resistance Suitable for installation over underfloor heating	EN 12664	0,11 m²*K/W		
	Formaldehyde (E1 = 0.1 ppm)	EN 16516	≤ 0.05 ppm		
			Lacquer	Natural oiled	untreated
	Reaction to fire	EN 13501-1	Dfl-s1		Dfl-s1 (CWFT)
	Chemical resistance	EN 13442	Category 5	Category 3	NPD
	Bond strength / Cross cutting test	ISO 2409	Category 1	n.n.	NPD
Free sorting according to EN 13489					
Type of wood:		Oak			
Botanical name / Code (EN 13556):		Quercus petraea Liebl., Quercus robur L., spp / QCXE			
Sorting:		Natur			
Features (Upper side of each lamella) „Features shall be measured according to EN 1310“					
Sound sapwood		not permitted			
Knot (intergrown)		permitted: up to 15mm			
Broken knots		not permitted			
Falling out knot		permitted: up to 3mm also cluster of knots			
Pinknots		permitted			
Slight splits, hairline		permitted: no end cracks (up to 5mm)			
Bark pocket		not permitted			
Lightning cracks		permitted			
Slope of grain		permitted			
Medullary ray		permitted			
Discoloration, colour variation		allowed: uniform colours with slight differences			
White streaks		not permitted			
Pilling sticks marking		not permitted			
Biodeterioration (EN 1311)		not permitted			
Non-visible parts					
All the features without restrictions on size or length permitted provided they do not affect the strength or durability of the soil.					
Comment					
Maximum 3% of lamellas are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master					
Changed:	QMB	File name:	PA TDS Parkett Trendtime-11&12 Tafelparkett EI EN 20250401		
Date:	01.08.2013	Update:	https://parador.de/en/services/downloads/engineered-wood-flooring		
Our TDS are constantly updated and adapted to the state of art. This version supersedes all earlier versions and is valid from: 01.04.2025					