

Product properties		
Format	3000 x 300 x 19mm	
Packaging	Pack:	4 Elements / 3,6 m ² / 35,468 kg
	Pallet:	28 Packs / 100,8 m ² / 993,104 kg
Notes	- only suitable for all-over adhesion - cleaning and maintenance see instructions - technical changes reserved	
Guarantee (according to Parador guarantee conditions)	25 years (private use) 10 years (commercial use)	

Tolerance (EN 13489)	
Admissible difference in length	± 0.1 %
Admissible difference in width	± 0.2 mm
Squareness of the element	≤ 0.2 %
Longitudinal curvature along the element	≤ 0.1 %
Transverse curvature across the width	≤ 0.2 %
Height differences of elements	≤ 0.2 mm
Moisture content at the time of first delivery (5-9%)	5 - 9%
Top layer	~ 3.5 mm

Product labelling				
 EN 14342:2013		 www.blauer-engel.de/uz176	 FSC® C018498 The mark of responsible forestry	

Classification general product features and surface characteristics				
		Test method	Rating / Information	
	Profile		T & G	
	Resistance to roller castor chairs	EN 425	We recommend the use of a conventional chair mat	
	Thermal resistance Suitable for installation over underfloor heating.	EN 12664	0.135 m ² *K/W	
	Formaldehyde (E1 = 0.1 ppm)	EN 16516	≤ 0.05 ppm	
			Lacquer	Natural oiled untreated
	Reaction to fire	EN 13501-1	D _{fl} -s1	
	Chemical resistance	EN 13442	Category 5	Category 3
	Bond strength / Cross cutting test	ISO 2409	Category 1	n.n.

Free sorting according to EN 13489	
Type of wood (top layer):	Oak
Botanical name / Code (EN 13556):	Quercus petraea Liebl., Quercus robur L., spp / QCXE
Internal abbreviation:	AFP XXL plank-EI / N6 / 20240801
Grade:	Rustikal
Features (upper side of each plank) „Features shall be measured according to EN 1310“	
Sound sapwood	not allowed
Knot (intergrown)	allowed: up to 80 mm
Durchfalläste	allowed: up to 60 mm
Pinknots	allowed: cluster of knots
Filling	allowed
Cracks / hairline cracks	allowed
Bark pocket	not allowed
Lightning cracks	allowed (in knots)
Slope of grain	no criteria
Medullary ray	allowed
Discoloration, colour variation	allowed: all colours
White streaks	allowed
Pilling sticks marking	not allowed
Biodeterioration (EN 1311)	not allowed
Non-visible parts	
All the features without restrictions on size or length permitted provided they do not affect the strength or durability of the soil.	
Comment	
Maximum 3% of planks are allowed in the next lower grading. Wood is a natural product and therefore different in colour and texture. Samples, brochures and photos are therefore only approximate and not binding. The action of sunlight affects the natural variation in wood shade. This allows the product present at the time of delivery of significant differences to master.	

Changed:	QMB	File name:	PA TDS Parkett Trendtime-6 EI EN 20250401
Date:	01.08.2013	Last update at:	https://parador.de/en/services/downloads/engineered-wood-flooring
Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from:			01.04.2025