

| Product quality |         |                                                              |                                                                |                                                                 |
|-----------------|---------|--------------------------------------------------------------|----------------------------------------------------------------|-----------------------------------------------------------------|
| Formats         |         | 840 x 140 x 9 mm<br>33.07" x 5.51" x 0.35"                   | 1285 x 194 x 8 mm<br>50.59" x 7.64" x 0.31"                    | 2200 x 235 x 8 mm<br>86.61" x 9.25" x 0.31"                     |
| Packaging       | Pack:   | 11 elements<br>1,294 m <sup>2</sup> / 13.92 sq ft<br>10,1 kg | 10 elements<br>2,493 m <sup>2</sup> / 26.83 sq ft<br>16.69 kg  | 6 elements<br>3,102 m <sup>2</sup> / 33.39 sq ft<br>20.87 kg    |
|                 | Pallet: | 56 packs<br>72,44 m <sup>2</sup> / 779,73 sq ft<br>580,6 kg  | 40 packs<br>99,72 m <sup>2</sup> / 1,073.38 sq ft<br>682.49 kg | 39 packs<br>120,98 m <sup>2</sup> / 1,302.21 sq ft<br>843.76 kg |

| Tolerances (Requirement EN 16511:2023)   |                               |                     |
|------------------------------------------|-------------------------------|---------------------|
| Squareness of the elements (≤ 0.50mm)    |                               | ≤ 0.15 mm           |
| Determination of Linearity (≤ 0.30 mm/m) |                               | ≤ 0.20 mm/m         |
| Flatness concave / convex                | lengthwise (≤ 0.50 / ≤ 1.0 %) | ≤ 0.35 / ≤ 1.0 %    |
|                                          | wide (≤ 0.10 / ≤ 0.15 %)      | ≤ 0.10 / ≤ 0.15 %   |
| Height difference                        | (average ≤ 0.15 mm)           | (average ≤ 0.10 mm) |
|                                          | (max. ≤ 0.20 mm)              | (max. ≤ 0.15 mm)    |
| Opening between installed elements       | (average ≤ 0.15 mm)           | (average ≤ 0.05 mm) |
|                                          | (max. ≤ 0.20 mm)              | (max. ≤ 0.10 mm)    |

| Guarantee (according Parador guarantee conditions) |                 | Notes                                               |
|----------------------------------------------------|-----------------|-----------------------------------------------------|
| Domestic area                                      | Commercial area | - suitable for all-over adhesion (up to max. 20sqm) |
| Lifetime                                           | 20 Years        | - cleaning and maintenance see instructions         |
|                                                    |                 | - technical changes reserved                        |









| Classification (acc. EN 16511:2023)                                                 |                                                                                                                            |                                                                                     |                                                                                                                                |
|-------------------------------------------------------------------------------------|----------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------------------------------|--------------------------------------------------------------------------------------------------------------------------------|
|    |                                                                                                                            |  |                                                                                                                                |
| Utility class 23 = domestic areas with intensive use                                |                                                                                                                            | Utility class 33 = commercial areas with intensive use                              |                                                                                                                                |
| The design floor meets all requirements of the designated use class.                |                                                                                                                            |                                                                                     |                                                                                                                                |
| Requirements / properties                                                           |                                                                                                                            | Test method                                                                         | Rating                                                                                                                         |
|   | Reaction to fire                                                                                                           | EN 13501-1                                                                          | C <sub>f</sub> s1                                                                                                              |
|  | Slip resistance                                                                                                            | EN 13893<br>EN 14041                                                                | μ ≥ 0.30<br>DS                                                                                                                 |
|  | Staining resistance                                                                                                        | EN 438-2                                                                            | Category 1 + 2: level 5, no visible change<br>Category 3: level 4, slight change                                               |
|  | Light fastness                                                                                                             | EN ISO 105 – B02                                                                    | Blue wool scale: Stage ≥ 6                                                                                                     |
|  | Resistance to roller castor chairs                                                                                         | EN ISO 4918                                                                         | Type W, no visible changes<br>(25,000 rev.)                                                                                    |
|  | <b>Thermal resistance</b><br>Suitable for installation over underfloor heating when using an appropriate moisture barrier. | EN 12667                                                                            | 0.075 m²·K/W                                                                                                                   |
|  | Moving a furniture leg                                                                                                     | EN ISO 16581                                                                        | No visible damage (foot type 0)                                                                                                |
|  | Residual indentation                                                                                                       | EN ISO 24343-1                                                                      | ≤ 0.05 mm                                                                                                                      |
|  | Formaldehyde emission (E1 = 0.1 ppm)                                                                                       | ISO 16000                                                                           | ≤ 0.05 ppm                                                                                                                     |
|  | Acoustical - Impact noise reduction                                                                                        | EN ISO 10140-3                                                                      | 18 dB (auf PE-Folie)                                                                                                           |
|  | Locking strength                                                                                                           | ISO 24334                                                                           | lengthwise ≥ 1 kN/m<br>transversely ≥ 1,5 kN/m<br>Herringbone<br>transversely * kN/m<br>(* not reportable due to construction) |
|  | Abrasion                                                                                                                   | ISO 24338, Annex B                                                                  | > 7,000 rev.                                                                                                                   |
|  | Impact resistance                                                                                                          | EN 13329 Annex F                                                                    | ≥ 1,800 mm                                                                                                                     |
|  | Dimensional stability after exposure to temperature                                                                        | EN ISO 23999                                                                        | ≤ 0.15 %                                                                                                                       |
|                                                                                     | Water resistance                                                                                                           | ISO 4760                                                                            | Requirements met (100h instead of 24h)<br>Herringbone (1h instead of 24h)                                                      |
|                                                                                     | Micro scratch resistance                                                                                                   | EN 16094                                                                            | Method A MSR-A2<br>For mat surfaces (gloss ≤ 7):<br>≤ 1.5 unit change at 60°                                                   |
|                                                                                     | Slip resistance                                                                                                            | EN 16165, Annex B<br>on an inclined plane                                           | R10                                                                                                                            |
|                                                                                     |                                                                                                                            | EN 16165, Annex C<br>pendulum test                                                  | PTV (dry (slider 96)) ≥ 36<br>Low slip potential<br>according to UK Slip resistance group                                      |
|                                                                                     | Disposal                                                                                                                   | EAK-Code-number                                                                     | 17 09 04                                                                                                                       |

|                                                                                                                                                      |             |                   |                                                                                                                                 |
|------------------------------------------------------------------------------------------------------------------------------------------------------|-------------|-------------------|---------------------------------------------------------------------------------------------------------------------------------|
| Changed:                                                                                                                                             | QMB Parador | File:             | PA_TDS_Taterra Click_EN_20260601                                                                                                |
| Date:                                                                                                                                                | 01.01.2026  | Latest update at: | <a href="https://parador.de/en/services/downloads/design-flooring">https://parador.de/en/services/downloads/design-flooring</a> |
| Our technical data sheets are constantly updated and adapted to the latest technology. This version replaces all earlier versions and is valid from: |             |                   | 01.06.2026                                                                                                                      |