



**XL FLOORING**

*Foundation Plank* 

SPECIFICATIONS

Item	Spec
Width	7" (178 mm)
Length	48" (1,219 mm)
Thickness	3.0 mm (1/8")
Wear Layer Thickness	0.5 mm (20mil)
Profile	Micro-beveled
Sq.Ft. per Carton	35 sq. ft (3.25 sq.m)
Planks per Carton	15
Weight per Carton	34.44 lbs (15.6 kg)
Cartons per Pallet	65
Sq.Ft. per Pallet	2,275 sq.ft (211.35 sq.m)
Weight per Pallet	2,238.6 lbs. (1,015.41 kg)
Type & Composition	PVC Laminate Floor Covering
Application	Residential & Commercial
Surface Treatment	Duracoat Polyurethane, anti-microbial, embedded with micro-ceramic beads
Visual Pattern Repeat	Please contact us for details
Backing	Dry Backing
Warranty	10 Year Limited Commercial

TEST RESULTS

Product testing carried out by independant testing labs.

Item	Spec/Test	Result
Dimensional Stability	ASTM F2199	.0038% inch/foot
Sound Absorbtion	IIC RATING/STC RATING	40/48
Use with Underfloor Radiant Heating	Recommended	
Floorscore Testing	Floorscore Certified	

## TEST RESULTS cont'd

Item	Spec/Test	Result
Emmissions German Dibit Results	TVOC after 3 days	0.095 parts/million
	TVOC after 28 days	0.005 parts/million
	SVOC after 28 days	0.005 parts/million
	Phenol after 28 days	0.000 parts/million
Critical Radiant Flux	ASTM E648-06 Mekol Burner Test	0.99 watts/cm <sup>2</sup> Pass
Light Resistance	ASTM F1515	6.0
Heat Stability	ASTM 1514	4.3
Slip Resistance	AS 4586 (CSIRO): Classification Walking Angle ADA	R=10 (meets commercial standard} 16° exceeds ADA requirement
Abrasian Resistance	ASTM D3884	0.003% @ 1000 cycles
Stain & Chemical Resistance	KSM 3802 - 24 Hour Exposure	95% ethyl Alcohol    0    Tea                    0
		Cement Paste        0    Ketchup             0
		10% ammonium     0    Nitric Acid         1
		hydroxide            0    Sulfuric Acid 95%  1
		Kerosene             0    Acetone             2
		Sesame Oil           0    Nail Polish         1
		Soy Sauce            0    Remover             2
		Soy Bean Oil         0    Methylene           1
		Lubricant            0    Chloride             2
		Coffee                0
Deflection	ASTM F1304	55.29 mm
Reaction to Fire Testing	EN 13501 1	<b>Requirement: max. extent of flame, ≤ 150 mm*</b> 1/1 to 1/5                    fulfilled 2/1 to 3/2                    fulfilled
Smoke Density - Flaming	ASTM E662	280 (Corrected to Max Density)
Smoke Density - Non-Flaming	ASTM E662	417 (Corrected to Max Density)
Short Term Indentation	ASTM F1914	0.008"
Static Load 1,000 PSI	ASTM F970	0.008° of residual indentation
Static Coefficient of Friction	ASTM D2047	Dry: 0.60
	ASTM C1028	Dry: 0.7144 Wet: 0.8900
Rolling Chair 25,000 hours	ASTM F2753	Negligible Disturbance
Phthalate Content - Negligible	Our plasticizers do not contain Phthalates. However, we do use post consumer recycled product in our flooring and there may be trace amounts of Phthalate in that recycled material. The tested content of Phthalate in our flooring is far less than government permissible standards (less than 1,000mg/kg of di(2-ethylhexyl) phthalate(DE-HP), dibutyl phthalate (DBH) or benzyl butyl phthalate (BBP).	

\*For end use application as a horizontal floor covering installed on mineral subfloor according to EN 13238:2010, using adhesives or not.

Critical heat flow ≥ 3.0 kW/m <sup>2</sup>	Fire class Dfl
Critical heat flow ≥ 4.5 kW/m <sup>2</sup>	Fire class Cfl
Critical heat flow ≥ 8.0 kW/m <sup>2</sup>	Fire class Bfl